

Mirathane™ H190

Thermoplastic Polyurethane Elastomer

Miracll Chemicals Co., Ltd.

Message:

Mirathane™ H190 is a Thermoplastic Polyurethane Elastomer product. It is available in Asia Pacific.

General Information			
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.20	g/cm ³	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	97		ASTM D2240
Elastomers	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	40.0	MPa	ASTM D412
Tensile Elongation (Break)	400	%	ASTM D412
Tear Strength	110	kN/m	ASTM D624
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	130	°C	ASTM D6493
Tfb	70	°C	
Tack Time	6.0	min	
Crystallization Rate	very fast		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

