

# HiPrene® HSG41

Polypropylene

GS Caltex

## Message:

HiPrene® HSG41 is 10% short glass fibre reinforced polypropylene compound. This grade has very good mechanical and thermal properties. It is suitable for many different applications in Automotive and Home appliance industry where it is necessary to have high stiffness.

General Information			
Filler / Reinforcement	Glass Fiber, 10% Filler by Weight		
Features	High Heat Resistance		
	High Stiffness		
Uses	Appliance Components		
	Automotive Applications		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	0.990 to 1.03	g/cm <sup>3</sup>	ISO 1183
Melt Mass-Flow Rate (MFR) <sup>1</sup>	4.0 to 8.0	g/10 min	ISO 1133
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	93		ISO 2039-2
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress	60.0	MPa	ISO 527-2/1A/50
Flexural Modulus	3400	MPa	ISO 178/B
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength (23°C)	9.0	kJ/m <sup>2</sup>	ISO 180/A
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	156	°C	ISO 75-2/A
NOTE			
1.	Procedure A		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

### Susheng Import & Export Trading Co., Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT