

4TECH® 9A22150 M

Polyamide 66

4Plas

Message:

4TECH 9A22150 M is a Standard Flow 50% Glass Fibre Reinforced MOSO2 Lubricated PA66

General Information			
Filler / Reinforcement	Glass fiber reinforced material, 50% filler by weight		
Additive	Lubricant		
Features	Lubrication		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.60	g/cm ³	ISO 1183
Water Absorption ¹ (Equilibrium, 23°C, 50% RH)	1.3	%	ISO 62
Moisture Content	< 2000	ppm	ISO 960
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	16000	MPa	ISO 527-2/5
Tensile Stress (Break, 23°C)	210	MPa	ISO 527-2/5
Tensile Strain (Break, 23°C)	2.5	%	ISO 527-2/5
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ISO 180/1A
-30°C	13	kJ/m ²	ISO 180/1A
23°C	15	kJ/m ²	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, not annealed	260	°C	ISO 75-2/B
1.8 MPa, not annealed	250	°C	ISO 75-2/A
Melting Temperature ²	262	°C	ISO 11357
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+13	ohms	IEC 60093
Volume Resistivity	1.0E+15	ohms · cm	IEC 60093
Comparative Tracking Index	500	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.60 mm)	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	80.0	°C	
Drying Time	2.0	hr	
Suggested Max Moisture	0.20	%	
Processing (Melt) Temp	270 - 300	°C	

Mold Temperature	70.0 - 110	°C
Injection Rate	Fast	
Holding Pressure	50.0 - 100	MPa
Screw Speed	200	rpm

Injection instructions

Feed Throat Temperature: 60 - 80 °CBack Pressure: Low

NOTE

- | | |
|----|----------|
| 1. | 24 Hrs |
| 2. | 10 K/min |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT