

Comco PEEK

Polyetheretherketone

Comco-Plastic GmbH

Message:

Comco PEEK is a Polyetheretherketone (PEEK) material. It is available in Europe. Primary attribute of Comco PEEK: Flame Rated.

General Information			
Appearance	Black		
	Natural Color		
Physical	Nominal Value	Unit	Test Method
Density	1.31	g/cm³	ISO 1183
Water Absorption			
Saturation, 23°C	0.45	%	ISO 62
Equilibrium, 23°C, 50% RH	0.20	%	
Water Absorption			
after 24 h immersion in water : 23°C	5.0	mg	
after 96 h immersion in water : 23°C	10.0	mg	
Maximum Service Temperature			
in air continuously	250	°C	
in air for short periods	310	°C	
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	105		ISO 2039-2
Ball Indentation Hardness	230	MPa	ISO 2039-1
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	4400	MPa	ISO 527-2
Tensile Stress (Yield, 23°C)	110	MPa	ISO 527-2
Tensile Strain (Break, 23°C)	20	%	ISO 527-2
Compressive Stress			ISO 604
2% Strain	57.0	MPa	
1% Strain	29.0	MPa	
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	3.5	kJ/m²	ISO 179/1eA
Charpy Unnotched Impact Strength	No Break		ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	160	°C	ISO 75-2/A
Melting Temperature	340	°C	
CLTE - Flow			
23 to 60°C	5.0E-5	cm/cm/°C	

23 to 100°C	5.0E-5	cm/cm/°C	
Thermal Conductivity	0.25	W/m/K	
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	> 1.0E+13	ohms	IEC 60093
Volume Resistivity	> 1.0E+14	ohms·cm	IEC 60093
Electric Strength	24	kV/mm	IEC 60243-1
Relative Permittivity			IEC 60250
100 Hz	3.20		
1 MHz	3.20		
Dissipation Factor			IEC 60250
100 Hz	1.0E-3		
1 MHz	2.0E-3		
Comparative Tracking Index	150	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
3.00 mm	V-0		
6.00 mm	V-0		
Oxygen Index	35	%	ISO 4589-2

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

