

ULTEM™ 2410EPR resin

Polyether Imide
SABIC Innovative Plastics

Message:

40% Glass fiber filled, high flow Polyetherimide (Tg 217C) with internal mold release for enhanced electroplatability. ECO Conforming, UL94 V0 listing.

General Information			
UL YellowCard	E121562-221105		
Filler / Reinforcement	Glass Fiber,40% Filler by Weight		
Additive	Mold Release		
Features	ECO Compliant		
	Platable		
Agency Ratings	EU Eco		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.56	g/cm³	ASTM D792, ISO 1183
Melt Mass-Flow Rate (MFR) (337°C/6.6 kg)	8.9	g/10 min	ASTM D1238
Melt Volume-Flow Rate (MVR) (360°C/5.0 kg)	11.0	cm³/10min	ISO 1133
Molding Shrinkage			Internal Method
Flow ¹	0.20 to 0.40	%	
Flow : 3.20 mm	0.20 to 0.40	%	
Across Flow : 3.20 mm	0.30 to 0.50	%	
Water Absorption			ISO 62
Saturation, 23°C	0.80	%	
Equilibrium, 23°C, 50% RH	0.40	%	
Hardness	Nominal Value	Unit	Test Method
Ball Indentation Hardness (H 358/30)	165	MPa	ISO 2039-1
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ²	11100	MPa	ASTM D638
--	11000	MPa	ISO 527-2/1
Tensile Strength			
Yield ³	165	MPa	ASTM D638
Yield	170	MPa	ISO 527-2/5
Break ⁴	165	MPa	ASTM D638
Break	170	MPa	ISO 527-2/5
Tensile Elongation			
Yield ⁵	1.8	%	ASTM D638

Yield	2.0	%	ISO 527-2/5
Break ⁶	1.8	%	ASTM D638
Break	2.0	%	ISO 527-2/5
Flexural Modulus			
50.0 mm Span ⁷	10700	MPa	ASTM D790
-- ⁸	9500	MPa	ISO 178
Flexural Stress			
--	220	MPa	ISO 178
Yield, 50.0 mm Span ⁹	240	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength ¹⁰			ISO 179/1eA
-30°C	10	kJ/m ²	
23°C	10	kJ/m ²	
Charpy Unnotched Impact Strength ¹¹			ISO 179/1eU
-30°C	35	kJ/m ²	
23°C	30	kJ/m ²	
Notched Izod Impact			
23°C	82	J/m	ASTM D256
-30°C ¹²	10	kJ/m ²	ISO 180/1A
23°C ¹³	10	kJ/m ²	ISO 180/1A
Unnotched Izod Impact			
23°C	410	J/m	ASTM D4812
-30°C ¹⁴	30	kJ/m ²	ISO 180/1U
23°C ¹⁵	30	kJ/m ²	ISO 180/1U
Instrumented Dart Impact (23°C, Total Energy)	18.0	J	ASTM D3763
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, Unannealed, 3.20 mm	212	°C	ASTM D648
0.45 MPa, Unannealed, 6.40 mm	215	°C	ASTM D648
0.45 MPa, Unannealed, 100 mm Span ¹⁶	208	°C	ISO 75-2/Be
0.45 MPa, Unannealed, 64.0 mm Span ¹⁷	206	°C	ISO 75-2/Bf
1.8 MPa, Unannealed, 3.20 mm	204	°C	ASTM D648
1.8 MPa, Unannealed, 6.40 mm	208	°C	ASTM D648
1.8 MPa, Unannealed, 100 mm Span ¹⁸	205	°C	ISO 75-2/Ae
1.8 MPa, Unannealed, 64.0 mm Span ¹⁹	197	°C	ISO 75-2/Af
Vicat Softening Temperature			
--	223	°C	ASTM D1525 ²⁰
--	214	°C	ISO 306/B50
--	215	°C	ISO 306/B120
Ball Pressure Test (125°C)	Pass		IEC 60695-10-2
CLTE			

Flow : -40 to 150°C	1.5E-5	cm/cm/°C	ASTM E831
Flow : 23 to 150°C	1.5E-5	cm/cm/°C	ISO 11359-2
Transverse : -40 to 150°C	4.5E-5	cm/cm/°C	ASTM E831
Transverse : 23 to 150°C	4.5E-5	cm/cm/°C	ISO 11359-2
Thermal Conductivity	0.30	W/m/K	ISO 8302
Electrical	Nominal Value	Test Method	
Arc Resistance ²¹	PLC 5	ASTM D495	
Comparative Tracking Index (CTI)	PLC 4	UL 746	
High Amp Arc Ignition (HAI)	PLC 4	UL 746	
High Voltage Arc Tracking Rate (HVTR)	PLC 4	UL 746	
Hot-wire Ignition (HWI)	PLC 4	UL 746	
Flammability	Nominal Value	Test Method	
Flame Rating (0.400 mm)	V-0	UL 94	
Injection	Nominal Value	Unit	
Drying Temperature	149	°C	
Drying Time	4.0 to 6.0	hr	
Drying Time, Maximum	24	hr	
Suggested Max Moisture	0.020	%	
Suggested Shot Size	40 to 60	%	
Rear Temperature	332 to 399	°C	
Middle Temperature	338 to 399	°C	
Front Temperature	343 to 399	°C	
Nozzle Temperature	343 to 399	°C	
Processing (Melt) Temp	349 to 399	°C	
Mold Temperature	135 to 163	°C	
Back Pressure	0.345 to 0.689	MPa	
Screw Speed	40 to 70	rpm	
Vent Depth	0.025 to 0.076	mm	
NOTE			
1.	Tensile Bar		
2.	5.0 mm/min		
3.	Type I, 5.0 mm/min		
4.	Type I, 5.0 mm/min		
5.	Type I, 5.0 mm/min		
6.	Type I, 5.0 mm/min		
7.	1.3 mm/min		
8.	2.0 mm/min		
9.	1.3 mm/min		
10.	80*10*4 sp=62mm		
11.	80*10*4 sp=62mm		
12.	80*10*4		
13.	80*10*4		

14.	80*10*4
15.	80*10*4
16.	120*10*4 mm
17.	80*10*4 mm
18.	120*10*4 mm
19.	80*10*4 mm
20.	Rate B (120°C/h), Loading 2 (50 N)
21.	Tungsten Electrode

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

