

SUPRAPLAST® UPA 54

Thermoset Polyester

RASCHIG GmbH

Message:

Glass-fibre reinforced Polyester moulding compound

Minimal mould shrinkage and post-shrinkage, very good arc resistance, very good mechanical strength

Contact terminals, relays, circuit breakers

This product meets the allowed upper limits for heavy metals and PCAs and also conforms to the requirements of the EU directives 2002/95 (RoHS), 2002/96 (WEEE) and 2006/122 (PFOS)

General Information			
Filler / Reinforcement	Glass Fiber		
Features	Arc Resistant		
	Good Strength		
	Low Shrinkage		
Uses	Electrical Parts		
Agency Ratings	EU 2002/96/EC (WEEE)		
	EU 2006/122/EC		
RoHS Compliance	RoHS Compliant		
Forms	Granules		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.90 to 2.10	g/cm ³	ISO 1183
Apparent Density	0.70 to 0.80	g/cm ³	ISO 60
Molding Shrinkage - Flow			ISO 2577
-- ¹	0.20 to 0.50	%	
-- ²	0.30 to 0.60	%	
Water Absorption (23°C, 24 hr)	< 0.50	%	ISO 62
Post Shrinkage ³	< 0.10	%	ISO 2577
Maximum Service Temperature			IEC 60216
<50 h	220	°C	
20,000 h	170	°C	
Compression Molding Molding Pressure	> 10.0	MPa	
Compression Molding Temperature	165 to 180	°C	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			ISO 527-2
Compression Molded	9000 to 11000	MPa	
Injection Molded	9000 to 11000	MPa	
Tensile Stress			ISO 527-2

Compression Molded	35.0 to 60.0	MPa	
Injection Molded	40.0 to 70.0	MPa	
Flexural Modulus			ISO 178
Compression Molded	10000 to 13000	MPa	
Injection Molded	13000 to 16000	MPa	
Flexural Stress			ISO 178
Compression Molded	80.0 to 100	MPa	
Injection Molded	100 to 120	MPa	
Compressive Stress	150 to 200	MPa	ISO 604
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
Compression Molded	2.5 to 3.5	kJ/m ²	
Injection Molded	3.5 to 5.0	kJ/m ²	
Charpy Unnotched Impact Strength			ISO 179/1eU
Compression Molded	5.0 to 10	kJ/m ²	
Injection Molded	8.0 to 11	kJ/m ²	
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (8.0 MPa, Unannealed)	> 200	°C	ISO 75-2/C
CLTE - Flow (50 to 100°C)	1.0E-5 to 2.0E-5	cm/cm/°C	ISO 11359-2
Thermal Conductivity	0.90 to 1.1	W/m/K	ASTM E1461
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+13 to 1.0E+14	ohms	IEC 60093
Volume Resistivity	1.0E+14 to 1.0E+15	ohms · cm	IEC 60093
Electric Strength	25 to 35	kV/mm	IEC 60243-1
Relative Permittivity			IEC 60250
	6.00		
100 Hz	5.00		
	5.00		
1 MHz	4.00		
Dissipation Factor			IEC 60250
100 Hz	0.010 to 0.030		
1 MHz	0.010 to 0.030		
Arc Resistance	PLC 4		ASTM D495
Comparative Tracking Index	600	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.50 mm)	V-0		UL 94
Glow Wire Flammability Index	960	°C	IEC 60695-2-12

Glow Wire Ignition Temperature	850	°C	IEC 60695-2-13
Injection	Nominal Value	Unit	
Middle Temperature	50.0 to 70.0	°C	
Front Temperature	80.0 to 100	°C	
Processing (Melt) Temp	100 to 115	°C	
Mold Temperature	165 to 180	°C	
Back Pressure	1.00 to 1.50	MPa	
Screw Speed	70 to 100	rpm	
NOTE			
1.	Compression Molded		
2.	Injection Molded		
3.	168 h / 110°C		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

