

# HydroThane™ 93A

Polyurethane

CardioTech International, Inc.

## Message:

HydroThane™ 93A is a Polyurethane material. It is available in North America for extrusion or injection molding.

Important attributes of HydroThane™ 93A are:

High Strength

Lubricated

General Information	
Additive	Lubricant
Features	High Elongation
	High Tensile Strength
	Lubricated
Forms	Pellets
Processing Method	Extrusion
	Injection Molding

Hardness	Nominal Value	Test Method	
Durometer Hardness (Shore A)	93	ASTM D2240	
Elastomers	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	53.8	MPa	ASTM D412
Tensile Elongation (Yield)	580	%	ASTM D412
Extrusion	Nominal Value	Unit	
Cylinder Zone 1 Temp.	76.7	°C	
Cylinder Zone 2 Temp.	85.0	°C	
Cylinder Zone 3 Temp.	87.8	°C	
Melt Temperature	79.4	°C	
Die Temperature	79.4	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT