

Versaflex™ FFC 2882-50

Thermoplastic Elastomer

PolyOne Corporation

Message:

Versaflex™ FFC 2882-50 is a model designed to pass some migration tests of fatty foods specified in European Food Standard 82/711/EEC. Versaflex™ FFC 2882-50 can be bonded or co-extruded with polypropylene

General Information			
Features	Compliance of Food Exposure		
Uses	overmolding Kitchen utensils Washer Non-specific food applications Container Consumer goods application field		
Agency Ratings	EU 82/711/EEC 10 days at 40C in 95% ethanol 2 EU 82/711/EEC 3 hrs at 60C in 95% ethanol 2		
RoHS Compliance	RoHS compliance		
Appearance	Translucent		
Forms	Particle		
Processing Method	Extrusion Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.898	g/cm ³	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 10 sec)	52		ASTM D2240
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress			ASTM D412
100% strain, 23°C	1.17	MPa	ASTM D412
300% strain, 23°C	2.12	MPa	ASTM D412
Tensile Strength (Break, 23°C)	6.60	MPa	ASTM D412
Tensile Elongation (Break, 23°C)	630	%	ASTM D412
Fill Analysis	Nominal Value	Unit	Test Method
Apparent Viscosity (200°C, 11200 sec ⁻¹)	39.7	Pa · s	ASTM D3835
Injection	Nominal Value	Unit	
Suggested Max Regrind	20	%	
Rear Temperature	193 - 204	°C	

Middle Temperature	199 - 216	°C
Front Temperature	204 - 227	°C
Nozzle Temperature	210 - 238	°C
Processing (Melt) Temp	204 - 227	°C
Mold Temperature	12.8 - 32.2	°C
Back Pressure	0.00 - 0.552	MPa
Screw Speed	50 - 100	rpm

Injection instructions

以聚丙烯(PP),乙烯-醋酸乙烯(EVA),或低密度的聚乙烯(LDPE)为载体的色母粒最适合用于Versaflex™ FFC 2882-50的着色.高流动性的色母粒(熔融指数在25-40克/10分钟)有助于提高颜色的分散.典型的色母粒添加重量比例为1%-5%.也可以使用色油进行着色,但以矿物油作为载体的色油对产品的最终硬度有显著的影响.不建议使用以PVC做载体的色母粒.如需高质量的颜色控制, GLS公司可以提供预着色产品.色母粒的适用性应由客户根据实际的试生产情况而最终确定.在使用前和后,都要用熔融指数在0.5-2.5的聚乙烯(PE)或聚丙烯(PP)进行彻底的清洗.在回收料没有污染的前提下,最高可以用20%比例的Versaflex™ FFC 2882-50 回收料和新料混和使用,同时不至于影响材料的特性.为尽可能降低对材料特性的影响和损耗,加工温度应尽可能的低.回收料的最终使用效果应由客户实际试生产情况决定.Versaflex™ FFC 2882-50

有优异的熔体稳定性.最大的停留时间因料筒尺寸差异而不同.一般在闲置8-10分钟或更长时间后,料筒内材料应被清空.该产品不需要干燥注射速度:

1-3英寸/秒一段: 注射压力: 500-700 psi二段: 保压压力: 10%-30%注射压力保压时间(厚部件):2-4秒保压时间(薄部件):1-2秒

Extrusion	Nominal Value	Unit
Melt Temperature	204 - 227	°C
Die Temperature	216 - 238	°C

Extrusion instructions

Rear: 380-400F Center: 390-420F Front: 400-440F Screw: 100-500rpm

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

