

Jackdaw PLA HT16WT6652

Polylactic Acid
Jackdaw Polymers

Message:

Jackdaw PLA HT16WT6652 is a Polylactic Acid (PLA) product. It is available in Europe. Primary characteristic: eco-friendly/green.

General Information			
Features		Renewable Resource Content	
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.35	g/cm ³	ASTM D792, ISO 1183
Melt Mass-Flow Rate (MFR) (170°C/2.16 kg)	0.75	g/10 min	ISO 1133
Molding Shrinkage	0.40	%	Internal Method
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	5900	MPa	ISO 527-2
Tensile Strength			ASTM D638, ISO 527-2
Yield	40.0	MPa	
Break	39.0	MPa	
Tensile Elongation			ASTM D638, ISO 527-2
Yield	1.0	%	
Break	1.5	%	
Flexural Modulus	4700	MPa	ASTM D790, ISO 178
Flexural Strength	50.0	MPa	ASTM D790, ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Unnotched Impact Strength ¹	8.50	kJ/m ²	ASTM D256
Charpy Unnotched Impact Strength	8.5	kJ/m ²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	50.0	°C	ASTM D648, ISO 75-2/A
Melting Temperature	148	°C	ISO 1218, ASTM D2117
NOTE			

1. Method A

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

