

OmniCarb™ PC/PBT 400IM2

Polycarbonate + PBT

OMNI Plastics, LLC

Message:

OmniCarb™ PC/PBT 400IM2 is a Polycarbonate + PBT (PC+PBT) product. It can be processed by injection molding and is available in North America. Characteristics include:
Flame Rated
Good UV Resistance
Impact Resistant
UV Stabilized

General Information			
UL YellowCard	E138590-222820		
Additive	UV Stabilizer		
Features	Good UV Resistance		
	Low Temperature Impact Resistance		
UL File Number	E138590		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.18	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	12	g/10 min	ASTM D1238
Molding Shrinkage			ASTM D955
Flow	0.50 to 1.1	%	
Across Flow	0.50 to 1.1	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield, 23°C)	51.7	MPa	ASTM D638
Tensile Elongation (Break)	120	%	ASTM D638
Flexural Modulus	1930	MPa	ASTM D790
Flexural Strength	82.7	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256
-30°C, 3.18 mm	640	J/m	
23°C, 3.18 mm	750	J/m	
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed, 3.18 mm)	96.0	°C	ASTM D648
Flammability	Nominal Value		Test Method
Flame Rating			UL 94
1.50 mm, Black	HB		
3.00 mm, Black	HB		
Injection	Nominal Value	Unit	

Drying Temperature	104 to 116	°C
Drying Time	2.0 to 4.0	hr
Suggested Max Moisture	0.020	%
Rear Temperature	227 to 243	°C
Middle Temperature	232 to 249	°C
Front Temperature	238 to 260	°C
Nozzle Temperature	238 to 260	°C
Processing (Melt) Temp	238 to 260	°C
Mold Temperature	48.9 to 82.2	°C
Back Pressure	0.345 to 0.689	MPa

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

