

FR-PET® CN3030SD

Polyethylene Terephthalate

Polyplastics Co., Ltd.

Message:

Flame Retardant, Standard, GF reinforced

General Information			
UL YellowCard	E213445-229179		
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
Additive	Flame Retardant		
Features	Flame Retardant		
UL File Number	E213445		
Forms	Pellets		
Part Marking Code (ISO 11469)	>PET-GF30 FR(17)<		
Physical	Nominal Value	Unit	Test Method
Density	1.65	g/cm ³	ISO 1183
Water Absorption (23°C, 24 hr)	0.20	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress	126	MPa	ISO 527-2
Tensile Strain (Break)	1.7	%	ISO 527-2
Flexural Modulus	9200	MPa	ISO 178
Flexural Stress	215	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	7.3	kJ/m ²	ISO 179/1eA
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	228	°C	ISO 75-2/A
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	7.0E+16	ohms·cm	IEC 60093
Electric Strength (3.00 mm)	18	kV/mm	IEC 60243-1
Comparative Tracking Index	200	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating	V-0		UL 94

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

