

INEOS PP R12C-00

Polypropylene Random Copolymer

INEOS Olefins & Polymers USA

Message:

R12C-00 is a clarified medium melt flow rate, and lightly antistatic polypropylene copolymer designed for injection molding and stretch blow molding end-use applications. This material meets the requirements of the U.S. Food and Drug Administration as specified in 21 CFR 177.1520.

General Information	
UL YellowCard	E31830-230780
Additive	Antistatic
	Clarifier
Features	Antistatic
	Food Contact Acceptable
	High Clarity
	Medium Flow
	Random Copolymer
Agency Ratings	EC 1907/2006 (REACH)
	FDA 21 CFR 177.1520
RoHS Compliance	Contact Manufacturer
Forms	Pellets
Processing Method	Injection Molding
	Stretch Blow Molding

Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.903	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	12	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	85		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹			ASTM D638
Yield	30.0	MPa	
Break	18.1	MPa	
Tensile Elongation ²			ASTM D638
Yield	13	%	
Break	200	%	
Flexural Modulus - 1% Secant	1140	MPa	ASTM D790A
Impact	Nominal Value	Unit	Test Method

Notched Izod Impact			ASTM D256
4°C	27	J/m	
23°C	64	J/m	
Notched Izod Impact (Area)			ASTM D256
4°C	3.60	kJ/m ²	
23°C	6.20	kJ/m ²	
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed)	80.0	°C	ASTM D648
Vicat Softening Temperature	131	°C	ASTM D1525
Optical	Nominal Value	Unit	Test Method
Gloss (60°)	95		ASTM D2457
Haze ³ (1270 μm)	12	%	ASTM D1003
NOTE			
1.	51 mm/min		
2.	51 mm/min		
3.	23°C		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

