

Taitalac® 8540H

Acrylonitrile Butadiene Styrene

Taita Chemical Company, Ltd.

Message:

Taitalac®8540H is an acrylonitrile butadiene styrene (ABS) material. This product is available in North America or Asia Pacific region. The processing method is injection molding.

Taitalac®The main features of 8540H are:

flame retardant/rated flame

Flame Retardant

Impact resistance

Typical application areas include:

Electrical/electronic applications

electrical appliances

business/office supplies

General Information			
UL YellowCard	E50263-241901		
Features	Impact resistance, high		
	Flame retardancy		
Uses	Computer components		
	Electrical appliances		
	Business equipment		
UL File Number	E50263		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.13	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR)			ASTM D1238
200°C/5.0 kg	3.0	g/10 min	ASTM D1238
220°C/10.0 kg	25	g/10 min	ASTM D1238
Molding Shrinkage - Flow	< 0.40	%	ASTM D955
Water Absorption (24 hr)	0.30	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	105		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹			ASTM D638
Yield, 23°C, 3.18mm	35.9	MPa	ASTM D638
Fracture, 23°C, 3.18mm	26.9	MPa	ASTM D638
Tensile Elongation ² (Break, 23°C, 3.18 mm)	20	%	ASTM D638
Flexural Modulus ³ (23°C)	2480	MPa	ASTM D790
Flexural Strength ⁴ (Yield, 23°C)	68.3	MPa	ASTM D790

Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256
23°C, 3.18 mm	210	J/m	ASTM D256
23°C, 12.7 mm	200	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed, 12.7 mm)	80.0	°C	ASTM D648
Vicat Softening Temperature	96.1	°C	ASTM D1525 ⁵
RTI Elec (1.57 mm)	60.0	°C	UL 746
RTI Imp (1.57 mm)	60.0	°C	UL 746
RTI (1.57 mm)	60.0	°C	UL 746
Electrical	Nominal Value	Unit	Test Method
High Amp Arc Ignition (HAI) (1.57 mm)	10.0		UL 746
High Voltage Arc Tracking Rate (HVTR) (1.57 mm)	81.3	mm/min	UL 746
Hot-wire Ignition (HWI) (1.57 mm)	40	sec	UL 746
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
1.59 mm	V-2		UL 94
3.18 mm	V-0		UL 94
Additional Information			
Water Absorption, ASTM D570: <0.3%			
Injection	Nominal Value	Unit	
Drying Temperature	80.0 - 85.0	°C	
Drying Time	2.0 - 4.0	hr	
Rear Temperature	180 - 210	°C	
Middle Temperature	195 - 220	°C	
Front Temperature	180 - 210	°C	
Nozzle Temperature	200 - 230	°C	
Processing (Melt) Temp	170 - 180	°C	
Mold Temperature	40.0 - 70.0	°C	
Injection Rate	Slow-Moderate		
Back Pressure	0.345 - 0.483	MPa	
Screw Speed	30 - 100	rpm	
Injection instructions			
Injection Pressure: Low Moderate to Moderately High			
NOTE			
1.	5.0 mm/min		
2.	5.0 mm/min		
3.	2.8 mm/min		
4.	2.8 mm/min		
5.	压力1 (10N)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

