Eltex® P KS350

Polypropylene Random Copolymer INEOS Olefins & Polymers Europe

Message:

Benefits & Features

ELTEX® P KS350 offers a very low heat seal temperature (10°C below that of ELTEX® P KS400 type random copolymers) and contains anti-block and slip additives. It is developed primarily for the sealing layer in "coextruded bioriented film" for food and technical packaging.

Applications

2nd generation terpolymer specially developed for sealing layer in "coextruded bioriented film" for food and technical packaging.

Features Uses	Antiblock Slip Antiblocking Food Contact Acceptable Low Temperature Heat Sealability Slip Terpolymer Bi-axially Oriented Film Film				
	Antiblocking Food Contact Acceptable Low Temperature Heat Sealability Slip Terpolymer Bi-axially Oriented Film Film				
	Food Contact Acceptable Low Temperature Heat Sealability Slip Terpolymer Bi-axially Oriented Film Film				
	Food Contact Acceptable Low Temperature Heat Sealability Slip Terpolymer Bi-axially Oriented Film Film				
Uses	Low Temperature Heat Sealability Slip Terpolymer Bi-axially Oriented Film Film				
Uses	Slip Terpolymer Bi-axially Oriented Film Film				
Uses	Terpolymer Bi-axially Oriented Film Film				
Uses	Bi-axially Oriented Film				
Uses	Film				
Uses	Film				
	Food Dackaging				
	Food Packaging				
	Packaging				
RoHS Compliance	Contact Manufacturer				
Forms	Pellets				
Processing Method	Coextrusion				
	Film Extrusion				
Physical	Nominal Value	Unit	Test Method		
Density (23°C)	0.895	g/cm³	ISO 1183		
Melt Mass-Flow Rate (MFR) (230°C/2.16					
kg)	5.0	g/10 min	ISO 1133		
Hardness	Nominal Value	Unit	Test Method		
Shore Hardness (Shore D, 23°C)	58 ISO 868		ISO 868		
Mechanical	Nominal Value	Unit	Test Method		
Tensile Stress (Yield, 23°C)	20.0 MPa ISO 527-2		ISO 527-2		
Flexural Modulus (23°C)	620	MPa	ISO 178		
Films	Nominal Value Unit Test Method		Test Method		
Heat Seal Threshold ¹		105 °C Internal Me			
Thermal		٣.	Internal Method		

Heat Deflection Temperature (0.45 MPa,					
Unannealed)	55.0	°C	ISO 75-2/B		
Vicat Softening Temperature	105	°C	ISO 306/A50		
Peak Melting Temperature	131	°C	ASTM D3417		
NOTE					

1s, 3 bars, 100 mm/min, 100 g/cm

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

1.

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

