

Zytel® 101F BKB009

NYLON RESIN
DuPont Performance Polymers

Message:
Unreinforced Polyamide 66

General Information			
UL YellowCard	E41938-100726136	E41938-234369	
Agency Ratings	UL Unspecified Rating		
Processing Method	Injection Molding		
Part Marking Code (ISO 11469)	>PA66<		
Resin ID (ISO 1043)	PA66		
Physical	Nominal Value	Unit	Test Method
Density	1.14	g/cm ³	ISO 1183
Molding Shrinkage			ISO 294-4
Across Flow	1.3	%	
Flow	1.4	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	3100	MPa	ISO 527-2
Tensile Stress (Yield)	82.0	MPa	ISO 527-2
Tensile Strain (Yield)	4.5	%	ISO 527-2
Nominal Tensile Strain at Break	18	%	ISO 527-2
Flexural Modulus	2800	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	5.5	kJ/m ²	ISO 179/1eA
Notched Izod Impact Strength			ISO 180/1A
-40°C	5.0	kJ/m ²	
23°C	5.5	kJ/m ²	
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	195	°C	ISO 75-2/B
1.8 MPa, Unannealed	70.0	°C	ISO 75-2/A
Melting Temperature ¹	262	°C	ISO 11357-3
Flammability	Nominal Value		Test Method
Flammability Classification			IEC 60695-11-10, -20
0.710 mm	V-2		
1.50 mm	V-2		
NOTE			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

