

# Veroplas PA3300

Polyamide 6

PlastxWorld Inc.

## Message:

Veroplas PA3300 is a polyamide 6 (nylon 6) product, which contains a 30% glass fiber reinforced material. It can be processed by injection molding and is available in North America or Europe.

General Information			
Filler / Reinforcement	Glass fiber reinforced material, 30% filler by weight		
Features	General		
Uses	General		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.36	g/cm <sup>3</sup>	ASTM D792
Molding Shrinkage - Flow	0.30	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	140	MPa	ASTM D638
Tensile Elongation (Break)	4.0	%	ASTM D638
Flexural Modulus	7520	MPa	ASTM D790
Flexural Strength	200	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	150	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	199	°C	ASTM D648
Vicat Softening Temperature	221	°C	ASTM D1525
Additional Information			
Glow Wire Test, UNE 20-672-83: 1200°F			
Injection	Nominal Value	Unit	
Suggested Max Moisture	0.17	%	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT