

OmniLon™ PA6/6 U IM20 HS BK1000

Polyamide 66

OMNI Plastics, LLC

Message:

Super High Impact, Heat Stabilized, Utility Grade, Nylon 6/6

General Information			
Additive	Heat Stabilizer		
Features	Heat Stabilized		
	High Impact Resistance		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.08	g/cm ³	ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield, 23°C)	48.3	MPa	ASTM D638
Tensile Elongation (Break)	40	%	ASTM D638
Flexural Modulus	1650	MPa	ASTM D790
Flexural Strength	62.1	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm)	850	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed, 3.18 mm	216	°C	
1.8 MPa, Unannealed, 3.18 mm	71.1	°C	
Flammability	Nominal Value	Test Method	
Flame Rating (3.18 mm)	HB	Internal Method	
Injection	Nominal Value	Unit	
Drying Temperature	79.4	°C	
Drying Time	2.0 to 4.0	hr	
Suggested Max Moisture	0.20	%	
Rear Temperature	260 to 293	°C	
Middle Temperature	271 to 293	°C	
Front Temperature	271 to 293	°C	
Nozzle Temperature	271 to 293	°C	
Processing (Melt) Temp	271 to 293	°C	
Mold Temperature	26.7 to 60.0	°C	
Back Pressure	0.345	MPa	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any

infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

