

Prime Polypro™ J-700GP

Polypropylene Homopolymer

Prime Polymer Co., Ltd.

Message:

Prime Polypro™ J-700GP is a Polypropylene Homopolymer (PP Homopolymer) product. It can be processed by injection molding and is available in Asia Pacific, Europe, or North America. Primary characteristic: homopolymer.

General Information			
UL YellowCard	E167245-526064		
Features	Homopolymer		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	0.900	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	8.0	g/10 min	ISO 1133
Molding Shrinkage	1.4 to 1.8	%	Internal Method
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	96		ISO 2039-2
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	1350	MPa	ISO 527-2
Tensile Stress (Yield)	33.0	MPa	ISO 527-2
Tensile Strain (Break)	20	%	ISO 527-2
Nominal Tensile Strain at Break	200	%	ISO 527-2
Flexural Modulus	1400	MPa	ISO 178
Flexural Stress	41.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Unnotched Impact Strength (23°C)	4.2	kJ/m ²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (0.45 MPa, Unannealed)	93.0	°C	ISO 75-2/B
Optical	Nominal Value		Test Method
Gloss	80		ASTM D2457

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

