

REV Materials 8006-001

Polypropylene

REV Materials

Message:

5% halloysite dispersed in a polypropylene matrix suitable for injection molding applications.

General Information			
Filler / Reinforcement	Clay filler, 5.0% filler by weight		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.948	g/cm ³	ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	1930	MPa	ASTM D638
Tensile Strength	33.1	MPa	ASTM D638
Tensile Elongation (Break)	5.8	%	ASTM D638
Flexural Modulus	1720	MPa	ASTM D790
Flexural Strength	51.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	16	J/m	ASTM D256
Unnotched Izod Impact	320	J/m	ASTM D256
Injection	Nominal Value	Unit	
Rear Temperature	149 - 232	°C	
Middle Temperature	149 - 232	°C	
Front Temperature	149 - 232	°C	
Nozzle Temperature	149 - 232	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT