

SLOVAMID® 66 T 35 FRY 7

Polyamide 66

Plastcom

Message:

PA 66 for injection moulding, chemically reinforced with 35 % mineral filler and non-halogen flame retardant, with heat resistance and nonflammability, achieves V 0 /3.2 mm/ in accordance with UL 94. Nonhalogen flame retardant guarantees excellent electric parameters like eg. electric strength and CTI. Application in electrotechnical industry: breakers, coil forms, covers, terminals.

General Information			
Filler / Reinforcement	Mineral,35% Filler by Weight		
Additive	Flame Retardant		
	Heat Stabilizer		
Features	Chemically Coupled		
	Flame Retardant		
	Good Electrical Properties		
	Halogen Free		
	Heat Stabilized		
	High Heat Resistance		
Uses	Electrical/Electronic Applications		
Appearance	Black		
	Colors Available		
	Natural Color		
Processing Method	Injection Molding		
Resin ID (ISO 1043)	PA 66		
Physical	Nominal Value	Unit	Test Method
Density	1.58	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (275°C/0.325 kg)	5.0	g/10 min	ISO 1133
Molding Shrinkage			STM 64 0808
Across Flow	0.62	%	
Flow	0.52	%	
Water Content	0.10	%	ISO 960
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	8950	MPa	ISO 527-2
Tensile Stress (Yield)	80.0	MPa	ISO 527-2
Tensile Strain (Yield)	2.0	%	ISO 527-2
Flexural Modulus	8100	MPa	ISO 178
Flexural Stress	120	MPa	ISO 178

Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179
-20°C	1.5	kJ/m ²	
23°C	3.0	kJ/m ²	
Charpy Unnotched Impact Strength			ISO 179
-20°C	15	kJ/m ²	
23°C	20	kJ/m ²	
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (0.45 MPa, Unannealed)	210	°C	ISO 75-2/B
Vicat Softening Temperature	250	°C	ISO 306/B
Melting Temperature (DSC)	260	°C	ISO 3146
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+13	ohms	IEC 60093
Volume Resistivity	1.0E+17	ohms·cm	IEC 60093
Electric Strength	35	kV/mm	IEC 60243-1
Comparative Tracking Index	600	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.60 mm)	V-0		UL 94
Glow Wire Ignition Temperature	960	°C	IEC 60695-2-13
Injection	Nominal Value	Unit	
Drying Temperature	80.0	°C	
Drying Time	4.0	hr	
Processing (Melt) Temp	260 to 290	°C	
Mold Temperature	70.0 to 90.0	°C	
Injection Pressure	70.0 to 120	MPa	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT