

Tarnoform® 500 GF5

Acetal (POM) Copolymer

Grupa Azoty S.A.

Message:

Tarnoform® 500 GF5 there is 25% glass fibres reinforced injection-moulding grade with high strength and stiffness and with reduced shrinkage and coefficient of linear thermal expansion, combined with higher flowability during moulding.

General Information			
Filler / Reinforcement	Glass Fiber,25% Filler by Weight		
Features	High Flow		
	High Stiffness		
	High Strength		
	Low Shrinkage		
Uses	Automotive Applications		
	Electrical/Electronic Applications		
	Household Goods		
	Thin-walled Parts		
Appearance	Black		
	Colors Available		
	Natural Color		
Forms	Granules		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.59	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	8.0	g/10 min	ISO 1133
Melt Volume-Flow Rate (MVR) (190°C/2.16 kg)	6.00	cm ³ /10min	ISO 1133
Molding Shrinkage			ISO 294-4
Across Flow : 2.00 mm	1.4	%	
Flow : 2.00 mm	0.80	%	
Water Absorption			ISO 62
Saturation, 23°C	0.80	%	
Equilibrium, 23°C, 50% RH	0.17	%	
Hardness	Nominal Value	Unit	Test Method
Ball Indentation Hardness (H 358/30)	205	MPa	ISO 2039-1
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	8900	MPa	ISO 527-2/1

Tensile Stress (Yield)	110	MPa	ISO 527-2/5
Tensile Strain (Break)	1.8	%	ISO 527-2/5
Flexural Modulus ¹	8000	MPa	ISO 178
Flexural Stress ²	155	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	5.0	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength	25	kJ/m ²	ISO 179/1eU
Notched Izod Impact Strength	5.0	kJ/m ²	ISO 180
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	160	°C	ISO 75-2/A
Vicat Softening Temperature	155	°C	ISO 306/B
Melting Temperature	167	°C	ISO 11357-3
CLTE			ISO 11359-2
Flow : 23 to 55°C	4.0E-5	cm/cm/°C	
Transverse : 23 to 55°C	8.0E-5	cm/cm/°C	
Limit of Temperature - a few hours operation	100	°C	
Burning Rate	< 100	mm/min	FMVSS 302
ISO Type	POM-K, M-GNR, 03-003, GF25		ISO 1874
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+13	ohms	IEC 60093
Volume Resistivity	1.0E+14	ohms·cm	IEC 60093
Electric Strength (2.00 mm)	30	kV/mm	IEC 60243-1
Dielectric Constant (1 Hz)	4.20		IEC 60250
Dissipation Factor (1 Hz)	9.5E-3		IEC 60250
Comparative Tracking Index (Solution A)	600	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating (3.20 mm)	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	100 to 120	°C	
Drying Time	2.0 to 4.0	hr	
Suggested Max Moisture	< 0.10	%	
Suggested Max Regrind	10	%	
Processing (Melt) Temp	180 to 230	°C	
Mold Temperature	80.0 to 110	°C	
Injection Pressure	80.0 to 110	MPa	
Injection Rate	Slow-Moderate		
NOTE			
1.	2.0 mm/min		
2.	2.0 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any

infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

