

SUSTAMID 6 MO

Polyamide 6
Röchling Sustaplast SE & Co. KG

Message:

Product characteristics
High mechanical strength
High rigidity
High UV resistance
Typical fields of application
Mechanical engineering
Conveyor industry
Vehicle construction

General Information			
Features	Good UV Resistance		
	High Rigidity		
	High Strength		
Uses	Automotive Applications		
	Conveyors		
	Engineered Applications		
Physical	Nominal Value	Unit	Test Method
Density	1.14	g/cm ³	ISO 1183
Water Absorption (Equilibrium, 23°C, 50% RH)	3.0	%	ISO 62
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore D)	82		ISO 868
Ball Indentation Hardness	170	MPa	ISO 2039-1
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	3200	MPa	ISO 527-2
Tensile Stress (Yield)	80.0	MPa	ISO 527-2
Tensile Strain (Break)	> 50	%	ISO 527-2
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	> 3.0	kJ/m ²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	75.0	°C	ISO 75-2/A
Continuous Use Temperature			
-- 1	-40.0 to 85.0	°C	
-- 2	< 160	°C	
Melting Temperature	220	°C	ISO 11357-3
CLTE - Flow	9.0E-5	cm/cm/°C	DIN 53752

Specific Heat	1700	J/kg/°C	DIN 52612
Thermal Conductivity	0.23	W/m/K	DIN 52612
Flammability	Nominal Value		Test Method
Flame Rating			UL 94
3.00 mm	HB		
6.00 mm	HB		
NOTE			
1.	Long Term		
2.	Short Term		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

