## RapidVac™ VA-1800

Polyurethane Thermoset Elastomer

Innovative Polymers, Inc.

## Message:

VA-1800 is a 80 shore A polyurethane elastomer formulated for hand-batch processing, vacuum assisted processing or meter mix dispensed. Excellent physical properties can be obtained with a room temperature cure without the utilization of mercury. MOCA, or TDI. VA-1800 has excellent green strength for quick demold times.

General Information					
Features	Good Green Strength				
RoHS Compliance	RoHS Compliant				
Appearance	Off-White				
Processing Method	Vacuum Casting				
Physical	Nominal Value	Unit	Test Method		
Specific Gravity					
Hardener	1.06	g/cm³			
Cured	1.12	g/cm³			
Base Resin	1.18	g/cm³			
Molding Shrinkage - Flow	0.20 to 0.50	%	ASTM D2566		
Thermoset	Nominal Value	Unit	Test Method		
Thermoset Components					
	Mix Ratio by Volume: 100				
Hardener	Mix Ratio by Weight: 100				
	Mix Ratio by Weight: 80				
Resin	Mix Ratio by Volume: 72				
Demold Time	30 to 60	min			
Uncured Properties	Nominal Value	Unit	Test Method		
Viscosity					
25°C <sup>1</sup>	0.55	Pa·s			
25°C <sup>2</sup>	1.8	Pa·s			
25°C <sup>3</sup>	4.5	Pa∙s			
Curing Time <sup>4</sup>	25	hr			
Gel Time	4.0 to 6.0	min			
Cured Properties	Nominal Value	Unit	Test Method		
Shore Hardness (Shore A)	70 to 80		ASTM D2240		
Tensile Strength	6.21	MPa	ASTM D638		

Tensile Elongation at Break	100	%	ASTM D638	
Tear Strength	14.0	kN/m	ASTM D624	
NOTE				
1.	Hardener			
2.	Mixed			
3.	Resin			
4.	24 hours at 77°F + 1 hour at 150°F			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

