

UMG ABS® EX270

Acrylonitrile Butadiene Styrene

UMG ABS, Ltd.

Message:

UMG ABS® EX270 is an Acrylonitrile Butadiene Styrene (ABS) material. It is available in Asia Pacific or North America.

Important attributes of UMG ABS® EX270 are:

Flame Rated

RoHS Compliant

General Information			
UL YellowCard	E47016-237398		
RoHS Compliance	RoHS Compliant		
UL File Number	E47016		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Density (23°C)	1.05	g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR) (220°C/10.0 kg)	5.00	cm ³ /10min	ISO 1133
Molding Shrinkage - Flow (23°C)	0.60 to 0.80	%	ISO 294-4
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale, 23°C)	110		ISO 2039-2
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	2550	MPa	ISO 527-2
Tensile Stress (23°C)	47.0	MPa	ISO 527-2
Flexural Modulus ¹ (23°C)	2600	MPa	ISO 178
Flexural Stress ² (23°C)	77.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179
-30°C	10	kJ/m ²	
23°C	23	kJ/m ²	
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	80.0	°C	ISO 75-2/Af
CLTE - Flow	8.0E-5	cm/cm/°C	ISO 11359-2
Flammability	Nominal Value		Test Method
Flame Rating (1.50 mm)	HB		UL 94
NOTE			
1.	2.0 mm/min		
2.	2.0 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT