

FORMULA P ELAN 3003 UV

Polypropylene

Putsch Kunststoffe GmbH

Message:

FORMULA P ELAN 3003 UV is a polypropylene product. It is available in Europe.

General Information			
Physical	Nominal Value	Unit	Test Method
Density	0.900	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	8.0	g/10 min	ISO 1133
Molding Shrinkage	1.5 - 1.8	%	Internal method
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress			ISO 527-2
Yield	18.0	MPa	ISO 527-2
Fracture	17.0	MPa	ISO 527-2
Tensile Strain (Break)	> 400	%	ISO 527-2
Flexural Modulus	900	MPa	ISO 178
Flexural Stress (3.5% Strain)	37.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ISO 180
-20°C	7.0	kJ/m ²	ISO 180
23°C	35	kJ/m ²	ISO 180
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	58.0	°C	ISO 306/B
Additional Information			
Tensile Strength, ISO 527: 18 MPa			
Injection	Nominal Value	Unit	
Processing (Melt) Temp	200 - 230	°C	
Mold Temperature	20.0 - 40.0	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT