

YUNGSOX® PP 5050

Polypropylene Random Copolymer

Formosa Polypropylene

Message:

YUNGSOX® PP 5050 is a Polypropylene Random Copolymer (PP Random Copolymer) material. It is available in Asia Pacific.

Important attributes of YUNGSOX® PP 5050 are:

Copolymer

Good Sealability

Typical applications include:

Adhesives/Tapes

Film

Food Contact Applications

Wrap

General Information			
Features	Low Temperature Heat Sealability		
	Random Copolymer		
	Soft		
Uses	Adhesives		
	Film		
	Shrink Wrap		
Agency Ratings	FDA 21 CFR 177.1520		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Density	0.900	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	6.5	g/10 min	ISO 1133
Molding Shrinkage	1.3 to 1.7	%	Internal Method
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	85		ISO 2039-2
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	19.6	MPa	ISO 527-2
Tensile Strain (Break)	500	%	ISO 527-2
Flexural Modulus	588	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	150	J/m	ISO 180
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	80.0	°C	ISO 75-2/A
Vicat Softening Temperature	110	°C	ISO 306
Melting Temperature	133	°C	DSC

Optical	Nominal Value	Unit	Test Method
Haze (30.0 μm)	< 1.0	%	Internal Method

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

