

SIBUR Synthetic Rubber SBR-1500 Grade B

Styrene Butadiene Rubber

SIBUR, LLC

Message:

Styrene butadiene synthetic rubber SBR-1500 is essentially a styrene (23.5%) and butadiene (76.5%) copolymer obtained by emulsification method with the use of resin/fatty soaps. The polymer contains no nitrosamines and substances that may become a source of nitrosamines.
Product characteristics: Appearance - bale of dark-brown color; weight of a bale - (30 ± 1) kg; packing - a plastic container; shelf life - one (1) year since the date of manufacture.

General Information			
Additive	Antioxidant 2		
Appearance	Brown		
Forms	Bale		
Physical	Nominal Value	Unit	Test Method
Mooney Viscosity (ML 1+4, 100°C)	46 to 56	MU	ASTM D1646
Bound Styrene	22.5 to 24.5	%	Internal Method
Ash Content	< 0.50	%	ASTM D5289
Organic Acid	5.0 to 7.0	%	ASTM D5774
Soap - Organic Acid	< 0.30	%	ASTM D5774
Volatile Matter	< 0.80	%	ASTM D5668
Rheometer MDR 2000 ¹			ASTM D5289
Maximum Torque (MH) : 160°C	15.0 to 21.0	dNm	
Minimum Torque (ML) : 160°C	1.80 to 3.00	dNm	
Prevulcanization start time (ts1) : 160°C	2.2 to 4.5	min	
Time to 50% vulcanization (T'50) : 160°C	7.0 to 12.0	min	
Time to 90% vulcanization (T'90) : 160°C	13.0 to 21.0	min	
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress (300% Strain)	> 13.0	MPa	ASTM D3185
Tensile Strength (Yield)	> 22.5	MPa	ASTM D3185
Tensile Elongation (Break)	> 420	%	ASTM D3185
NOTE			

1. deformation of 0.5°, MH at 30 min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

