

LNP™ STAT-KON™ DX12411C compound

Polycarbonate

SABIC Innovative Plastics

Message:

LNP STAT-KON DX12411C is a compound based on Polycarbonate resin containing Proprietary Filler(s). Added features of this material include:

Electrically Conductive, Clean Compounding System.

Also known as: LNP* STAT-KON* Compound DX12411C

Product reorder name: DX12411C

General Information			
Filler / Reinforcement	Proprietary		
Features	Electrically Conductive		
	Low (to None) Ion Content		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.25	g/cm ³	ASTM D792
Molding Shrinkage			ASTM D955
Flow : 24 hr	0.85	%	
Across Flow : 24 hr	1.0	%	
Water Absorption			
24 hr, 50% RH	0.15	%	ASTM D570
Equilibrium, 23°C, 50% RH	0.22	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	2630	MPa	ASTM D638
--	2570	MPa	ISO 527-2/1
Tensile Strength			
Yield ²	55.0	MPa	ASTM D638
Yield	54.0	MPa	ISO 527-2/5
Break ³	47.0	MPa	ASTM D638
Break	47.0	MPa	ISO 527-2/5
Tensile Elongation			
Yield ⁴	4.7	%	ASTM D638
Yield	4.6	%	ISO 527-2/5
Break ⁵	19	%	ASTM D638
Break	12	%	ISO 527-2/5
Flexural Modulus			
50.0 mm Span ⁶	2690	MPa	ASTM D790
-- ⁷	2540	MPa	ISO 178
Flexural Stress	88.8	MPa	ISO 178

Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			
23°C	300	J/m	ASTM D256
23°C ⁸	19	kJ/m ²	ISO 180/1A
Instrumented Dart Impact			
23°C, Total Energy	34.7	J	ASTM D3763
--	33.2	J	ISO 6603-2
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, Unannealed, 3.20 mm	139	°C	ASTM D648
0.45 MPa, Unannealed, 64.0 mm Span ⁹	138	°C	ISO 75-2/Bf
1.8 MPa, Unannealed, 3.20 mm	92.0	°C	ASTM D648
1.8 MPa, Unannealed, 64.0 mm Span ¹⁰	108	°C	ISO 75-2/Af
CLTE			ASTM D696
Flow : -30 to 30°C	7.1E-5	cm/cm/°C	
Transverse : -30 to 30°C	7.2E-5	cm/cm/°C	
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+3 to 1.0E+6	ohms	ASTM D257
Volume Resistivity	1.0E+3 to 1.0E+6	ohms · cm	ASTM D257
Injection	Nominal Value	Unit	
Drying Temperature	121	°C	
Drying Time	4.0	hr	
Suggested Max Moisture	0.020	%	
Rear Temperature	293 to 304	°C	
Middle Temperature	310 to 321	°C	
Front Temperature	321 to 332	°C	
Processing (Melt) Temp	304 to 327	°C	
Mold Temperature	82.2 to 110	°C	
Back Pressure	0.172 to 0.344	MPa	
Screw Speed	30 to 60	rpm	
NOTE			
1.	5.0 mm/min		
2.	Type I, 5.0 mm/min		
3.	Type I, 5.0 mm/min		
4.	Type I, 5.0 mm/min		
5.	Type I, 5.0 mm/min		
6.	1.3 mm/min		
7.	2.0 mm/min		
8.	80*10*4		
9.	80*10*4 mm		
10.	80*10*4 mm		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

