

Syncure™ V0044G RoHS Natural

Crosslinked Polyethylene

PolyOne Corporation

Message:

Flame retardant masterbatch catalyst composition, used in Polyvan Syncure system.

General Information			
Features	Flame retardancy		
Uses	Wire and cable applications		
Forms	Particle		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	2.25	g/cm ³	ASTM D792
Apparent Density ¹	1.26	g/cm ³	Internal method
Melt Mass-Flow Rate (MFR) ² (190°C/2.16 kg)	3.4	g/10 min	ASTM D1238
Additional Information			
离散度基于100 phr S1025A / 90 phr V0044G Syncure系统测量得出.在90摄氏度的水中硫化6小时.离散作用明显.外观颗粒为1/8"圆形.			
NOTE			
1.	Geon® 1169		
2.	Procedure A		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China


WECHAT