

RTP 2700 S-30A

Styrene Ethylene Butylene Styrene Block Copolymer

RTP Company

Message:

General Purpose

General Information			
Features	General Purpose		
Uses	General Purpose		
RoHS Compliance	Contact Manufacturer		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.890	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.20 mm)	2.0 to 3.0	%	ASTM D955
Moisture Content	0.040	%	
Peel Strength			
PP ¹	4.4	kN/m	
PP (30% VLF) ²	4.2	kN/m	
PP (50% VLF) ³	3.7	kN/m	
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 10 sec)	30		ASTM D2240
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress (100% Strain)	0.586	MPa	ASTM D412
Tensile Strength (Yield)	4.07	MPa	ASTM D412
Tensile Elongation (Yield)	660	%	ASTM D412
Tear Strength ⁴	17.9	kN/m	ASTM D624
Compression Set ⁵			ASTM D395B
23°C, 22 hr	12	%	
70°C, 22 hr	45	%	
Flammability	Nominal Value		Test Method
Flame Rating (1.50 mm, ** Values per RTP Company testing.)	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	71.1	°C	
Drying Time	2.0 to 4.0	hr	
Processing (Melt) Temp	163 to 204	°C	
Mold Temperature	15.6 to 37.8	°C	
Injection Pressure	34.5 to 68.9	MPa	
NOTE			
1.	90°, 20 in/min, RTP 55, Overmold Failure		

2.	90°, 20 in/min, RTP 55, Overmold Failure
3.	90°, 20 in/min, RTP 55, Interface Failure
4.	Die C
5.	Type 2

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

