

Trovidur® EN Liner red

Rigid Polyvinyl Chloride

Röchling Engineering Plastics SE & Co. KG

Message:

- Product characteristics
- Normal impact strength
- High chemical resistance
- Typical field of application
- Chemical engineering and tank building
- Ventilation manufacturing

General Information			
Features	Good Chemical Resistance		
Uses	Engineered Applications		
	Liners		
	Tanks		
Appearance	Red		
Physical	Nominal Value	Unit	Test Method
Density	1.47	g/cm³	ISO 1183
Water Absorption (Equilibrium, 23°C, 50% RH)	< 3.0	%	ISO 62
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore D)	85		ISO 868
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	3100	MPa	ISO 527-2
Tensile Strain (Break)	50	%	ISO 527-2
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	4.0	kJ/m²	ISO 179
Thermal	Nominal Value	Unit	Test Method
CLTE - Flow	6.0E-5 to 8.0E-5	cm/cm/°C	DIN 53752
Thermal Conductivity	0.16	W/m/K	DIN 52612
Heat Deflection Temperature - Vicat B	82	°C	ISO 306
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	> 1.0E+13	ohms	IEC 60093
Volume Resistivity	> 1.0E+15	ohms · cm	IEC 60093
Dielectric Constant	3.20		IEC 60250
Dissipation Factor (1 MHz)	0.020		IEC 60250
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
3.00 mm	V-0		
6.00 mm	V-0		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

