

Mapex AN2320SN

Polyamide 66/6 Copolymer

Ginar Technology Co., LTD.

Message:

Mapex AN2320SN is a polyamide 66/6 copolymer (nylon 66/6) product, which contains a 13% glass fiber reinforced material. It can be processed by injection molding and is available in North America, Africa and the Middle East, Europe or Asia Pacific. Mapex AN2320SN applications include the automotive industry and handles.

Features include:

Hard

Heat resistance

General Information			
Filler / Reinforcement	Glass fiber reinforced material, 13% filler by weight		
Features	Rigidity, high		
	Heat resistance, high		
Uses	Handle		
	Application in Automobile Field		
Appearance	Available colors		
	Natural color		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.23	g/cm ³	ASTM D792
Molding Shrinkage - Flow	0.40	%	ASTM D955
Water Absorption (24 hr)	1.2	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	121		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	103	MPa	ASTM D638
Tensile Elongation (Break)	1.8	%	ASTM D638
Flexural Modulus	4830	MPa	ASTM D790
Flexural Strength	138	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	53	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	220	°C	ASTM D648
Injection	Nominal Value	Unit	
Drying Temperature	70.0	°C	

Drying Time	4.0	hr
Suggested Max Moisture	0.20	%
Suggested Shot Size	40 - 80	%
Rear Temperature	250 - 265	°C
Middle Temperature	270 - 285	°C
Nozzle Temperature	265 - 275	°C
Mold Temperature	60.0 - 80.0	°C
Back Pressure	0.00 - 0.294	MPa
Screw Speed	50 - 70	rpm
Injection instructions		

Injection Pressure: 50 to 70% Injection Speed: 50 to 70%

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

