

Hostaform® EC140XF

Acetal (POM) Copolymer

Celanese Corporation

Message:

Hostaform® EC140XF is a conductive ESD grade of acetal copolymer for applications requiring dissipation of static build-up. EC140XF has an improved resistance to aggressive fuel blends.

General Information			
UL YellowCard	E38860-101233763		
Features	Conductivity		
	Electrostatic discharge protection		
	Fuel resistance		
RoHS Compliance	Contact manufacturer		
Physical	Nominal Value	Unit	Test Method
Density	1.42	g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR) (190°C/2.16 kg)	4.00	cm ³ /10min	ISO 1133
Molding Shrinkage			ISO 294-4
Vertical flow direction	1.9	%	ISO 294-4
Flow direction	2.1	%	ISO 294-4
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2700	MPa	ISO 527-2/1A/1
Tensile Stress (Yield)	53.0	MPa	ISO 527-2/1A/50
Tensile Strain			ISO 527-2/1A/50
Yield	4.7	%	ISO 527-2/1A/50
Fracture	12	%	ISO 527-2/1A/50
Flexural Modulus (23°C)	2650	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	4.0	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	70	kJ/m ²	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, not annealed	152	°C	ISO 75-2/B
1.8 MPa, not annealed	91.0	°C	ISO 75-2/A
Melting Temperature ¹	166	°C	ISO 11357-3
Linear thermal expansion coefficient			ISO 11359-2
Flow	1.0E-4	cm/cm/°C	ISO 11359-2
Lateral	1.1E-4	cm/cm/°C	ISO 11359-2
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+3	ohms	IEC 60093

Volume Resistivity	5.0E+2	ohms·cm	IEC 60093
Injection	Nominal Value	Unit	
Drying Temperature	80.0 - 100	°C	
Drying Time	3.0	hr	
Rear Temperature	170 - 180	°C	
Middle Temperature	180 - 190	°C	
Front Temperature	190 - 200	°C	
Nozzle Temperature	190 - 210	°C	
Processing (Melt) Temp	190 - 210	°C	
Mold Temperature	80.0 - 120	°C	
Injection Pressure	60.0 - 120	MPa	
Holding Pressure	60.0 - 120	MPa	
Back Pressure	0.00 - 0.500	MPa	
Injection instructions			
Manifold Temperature: 190 to 210°CZone 4 Temperature: 190 to 210°C			
NOTE			
1.	10°C/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT