

Kepamid® 2333GB

Polyamide 66

Korea Engineering Plastics Co., Ltd

Message:

KEPAMID 2333GB is a glass bubble 30%-filled and low specific gravity PA66 grade.

It is suitable for automotive, electrical & electronics parts requiring low specific gravity and dimensional stability.

General Information			
Filler / Reinforcement	Glass beads, 30% filler by weight		
Features	Low Specific Gravity		
	Good dimensional stability		
Uses	Electrical/Electronic Applications		
	Application in Automobile Field		
RoHS Compliance	RoHS compliance		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	0.938	g/cm ³	ISO 1183
shrinkage-Flow (3.00 mm)	1.0 - 1.2	%	Internal method
Water Absorption (Equilibrium, 23°C, 50% RH)	0.70	%	ISO 62
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	120		ISO 2039-2
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress	85.0	MPa	ISO 527-2
Tensile Strain (Break)	5.0	%	ISO 527-2
Flexural Modulus	4350	MPa	ISO 178
Flexural Stress	145	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	2.5	kJ/m ²	ISO 179/1eA
Thermal	Nominal Value	Unit	Test Method
Melting Temperature ¹	260	°C	ISO 11357-3
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+15	ohms · cm	IEC 60093
Relative Permittivity (1 MHz)	3.80		IEC 60250
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.8 mm)	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature			

--	90	°C
Dry Air Dryer	80	°C
Drying Time		
--	6.0 - 8.0	hr
Dry Air Dryer	4.0 - 6.0	hr
Suggested Max Moisture	0.050	%
Hopper Temperature	60 - 80	°C
Rear Temperature	280	°C
Middle Temperature	285	°C
Front Temperature	285	°C
Nozzle Temperature	290	°C
Mold Temperature	70 - 90	°C
Back Pressure	0.490 - 0.981	MPa
Screw Speed	80 - 120	rpm
NOTE		
1.	10°C/min	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

