

VITAMIDE® AR34BK8516

Polyamide 66
Jackdaw Polymers

Message:

VITAMIDE® AR34BK8516 is a Polyamide 66 (Nylon 66) product filled with 20% glass fiber. It is available in Europe. Primary characteristic: flame rated.

General Information			
Filler / Reinforcement	Glass Fiber,20% Filler by Weight		
Appearance	Black		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.29	g/cm³	ASTM D792, ISO 1183
Water Absorption (23°C, 24 hr)	1.0	%	ASTM D570, ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	140	MPa	ASTM D638, ISO 527-2
Tensile Elongation (Break)	4.0	%	ASTM D638, ISO 527-2
Flexural Modulus	6400	MPa	ASTM D790, ISO 178
Flexural Stress			
--	205	MPa	ISO 178
Break	205	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength	7.0	kJ/m²	ISO 180
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, Unannealed	255	°C	ASTM D648, ISO 75-2/B
1.8 MPa, Unannealed	250	°C	ASTM D648, ISO 75-2/A
Peak Melting Temperature	260	°C	ASTM D2117, ISO 1218
CLTE - Flow	3.0E-5	cm/cm/°C	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+15	ohms·cm	ASTM D257, IEC 60093
Dielectric Strength	32	kV/mm	ASTM D149, IEC 60243-1
Comparative Tracking Index (Solution A)	450	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating	HB		UL 94
Oxygen Index	24	%	ASTM D2863, ISO 4589-2

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

