

ACRYREX® CM-207G

Polymethyl Methacrylate Acrylic

CHI MEI CORPORATION

Message:

ACRYREX® CM-207G is a Polymethyl Methacrylate Acrylic product. It is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America.

Characteristics include:

Flame Rated

RoHS Compliant

General Information			
UL YellowCard	E56070-101126894		
RoHS Compliance	RoHS Compliant		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.19	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/3.8 kg)	9.0	g/10 min	ASTM D1238
Water Absorption (25°C, 24 hr)	0.30	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale, 6.35 mm)	90		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (3.18 mm)	71.6	MPa	ASTM D638
Tensile Elongation ² (Break, 3.18 mm)	10	%	ASTM D638
Flexural Strength ³ (6.35 mm)	114	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 6.35 mm)	12	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load ⁴ (1.8 MPa, Unannealed, 6.35 mm)	102	°C	ASTM D648
Vicat Softening Temperature	115	°C	ASTM D1525 ⁵
Flammability	Nominal Value		Test Method
Flame Rating (1.59 mm)	HB		UL 94
Optical	Nominal Value	Unit	Test Method
Transmittance (3180 μm)	93.0	%	ASTM D1003
NOTE			
1.	6.0 mm/min		
2.	6.0 mm/min		
3.	2.8 mm/min		
4.	120°C/hr		
5.	Rate A (50°C/h)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT