

Niblan V100 AE V0/M

Polybutylene Terephthalate

Soredi S.p.a.

Message:

Unreinforced PBT, impact modified and flame retardant

General Information			
Additive	Impact modifier		
Features	Impact modification		
	Flame retardancy		
Forms	Particle		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.38	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (250°C/2.16 kg)	30	g/10 min	ASTM D1238
Molding Shrinkage - Flow	1.0 - 2.2	%	ASTM D955
Water Absorption (23°C, 24 hr)	0.40	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	80		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (Yield)	50.0	MPa	ASTM D638
Tensile Elongation ² (Break)	10	%	ASTM D638
Flexural Modulus ³	2500	MPa	ASTM D790
Flexural Strength ⁴ (Break)	80.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256
-22°C, 3.20 mm	35	J/m	ASTM D256
23°C, 3.20 mm	80	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	60.0	°C	ASTM D648
Peak Crystallization Temperature (DSC)	220	°C	ASTM D3418
CLTE - Flow (23 to 55°C)	6.0E-5	cm/cm/°C	ISO 11359-2
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+15	ohms	IEC 60093
Volume Resistivity	1.0E+15	ohms · cm	IEC 60093
Dielectric Strength (1.00 mm)	30	kV/mm	IEC 60243-1
Relative Permittivity (1 MHz)	3.50		IEC 60250
Dissipation Factor (1 MHz)	0.0		IEC 60250
Flammability	Nominal Value	Unit	Test Method

Flame Rating		UL 94
1.60 mm	V-0	UL 94
3.20 mm	V-0	UL 94
Glow Wire Ignition Temperature (2.00 mm)	960	°C IEC 60695-2-13
Additional Information		
Volume Resistivity, IEC 60093: > 1E15 ohm-cmSurface Resistivity, IEC 60093: > 1E15 ohms		
NOTE		
1.	50 mm/min	
2.	50 mm/min	
3.	1.3 mm/min	
4.	1.3 mm/min	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT