

RTP 603 TFE 13 SI 2

Acrylonitrile Butadiene Styrene

RTP Company

Message:

Glass Fiber - PTFE Lubricated - Silicone Lubricated

General Information			
Filler / Reinforcement	Glass fiber reinforced material, 20% filler by weight		
Additive	PTFE lubricant (13%)		
	Silicone lubricant (2%)		
Features	Lubrication		
RoHS Compliance	Contact manufacturer		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.30	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.20 mm)	0.20 - 0.40	%	ASTM D955
Moisture Content	0.10	%	
Primary Additive	20	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	6550	MPa	ASTM D638
Tensile Strength	77.9	MPa	ASTM D638
Tensile Elongation (Yield)	1.0 - 2.0	%	ASTM D638
Flexural Modulus	6480	MPa	ASTM D790
Flexural Strength	121	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.20 mm)	53	J/m	ASTM D256
Unnotched Izod Impact (3.20 mm)	240	J/m	ASTM D4812
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	> 1.0E+14	ohms	ASTM D257
Volume Resistivity	> 1.0E+14	ohms · cm	ASTM D257
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.50 mm, ** Values per RTP Company testing.)	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	82.2	°C	
Drying Time	2.0	hr	
Dew Point	-17.8	°C	
Processing (Melt) Temp	204 - 238	°C	
Mold Temperature	62.8 - 85.0	°C	

Injection Pressure	68.9 - 103	MPa
Injection instructions		

Desiccant Type Dryer Required.

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

