

Lupoy® 1200-08

Polycarbonate
LG Chem Ltd.

Message:

LUPOY PC 1200-08 resin is designed for extrusion and injection molding products. It exhibits an excellent physical property balance of heat resistance, transparency and impact strength.

General Information			
UL YellowCard		E67171-100907358	
Features	Food Contact Acceptable		
	Good Impact Resistance		
	High Clarity		
	High Heat Resistance		
	High Purity		
	Medium Viscosity		
Uses	Disposable Tableware		
	Film		
	Lighting Diffusers		
	Packaging		
Agency Ratings	EU Food Contact, Unspecified Rating		
	FDA 21 CFR 177.1580		
RoHS Compliance	RoHS Compliant		
UL File Number	E306922		
Processing Method	Extrusion		
	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.20	g/cm³	ASTM D792
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	8.0	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.50 to 0.70	%	ASTM D955
Water Absorption			ASTM D570
23°C, 24 hr	0.15	%	
Equilibrium, 23°C, 50% RH	0.32	%	
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness			ASTM D785
M-Scale	73		
R-Scale	118		

Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2410	MPa	ASTM D638
Tensile Strength			ASTM D638
Yield, 23°C ¹	60.0	MPa	
Break	72.0	MPa	
Tensile Elongation			ASTM D638
Yield	6.0	%	
Break	150	%	
Flexural Modulus	2410	MPa	ASTM D790
Flexural Strength	96.0	MPa	ASTM D790
Taber Abrasion Resistance - Change in Haze ²	45	%	ASTM D1004
Average Extent of Burning	3	cm	ASTM D635
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact ³ (23°C, 3.20 mm)	900	J/m	ASTM D256
Unnotched Izod Impact (23°C)	No Break		ASTM D256
Instrumented Dart Impact ⁴ (23°C, 3.20 mm, Total Energy)	89.0	J	ASTM D3763
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Annealed, 4.00 mm	144	°C	
1.8 MPa, Unannealed, 4.00 mm	128	°C	
1.8 MPa, Annealed, 4.00 mm	141	°C	
Vicat Softening Temperature	150	°C	ASTM D1525 ⁵
Ball Indentation Temperature	> 125	°C	IEC 60598-1
CLTE - Flow (-40 to 82°C)	6.8E-5	cm/cm/°C	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity (23°C)	2.0E+17	ohms·cm	ASTM D257
Dielectric Strength	17	kV/mm	ASTM D149
Dielectric Constant (60 Hz)	3.00		ASTM D150
Dissipation Factor (60 Hz)	1.0E-3		ASTM D150
Comparative Tracking Index (2.00 mm)	250	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
3.00 mm	HB		
0.500 mm	V-2		
1.60 mm	V-2		
2.50 mm	V-2		
2.70 mm	V-2		
Glow Wire Ignition Temperature ⁶ (2.00 mm)	850	°C	IEC 60695-2-13
Oxygen Index	26	%	ASTM D2863
Optical	Nominal Value	Unit	Test Method

Refractive Index	1.586		ASTM D542
Transmittance	89.0	%	ASTM D1003
Haze	0.70 to 1.5	%	ASTM D1003
NOTE			
1.	50 mm/min		
2.	1000g, 500 cycles, CS-10F Wheel		
3.	0.25 mm Notch Depth		
4.	3.38 m/sec		
5.	Rate A (50°C/h), Loading 2 (50 N)		
6.	5 sec		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT