

WPP PP PPC5GF2-Natural

Polypropylene Copolymer
Washington Penn Plastic Co. Inc.

Message:

WPP PP PPC5GF2-Natural is a polypropylene copolymer (PP Copoly) product, which contains a 20% glass fiber reinforced material. It is available in North America, Africa and the Middle East, Latin America, Europe or Asia Pacific. Typical application areas are: automotive industry.

Features include:

Impact modification

heat stabilizer

General Information	
Filler / Reinforcement	Glass fiber reinforced material, 20% filler by weight
Additive	Impact modifier heat stabilizer
Features	Impact modification Thermal Stability
Uses	Application in Automobile Field Automotive exterior parts
Appearance	Available colors Natural color

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.03	g/cm ³	ASTM D792, ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	12	g/10 min	ASTM D1238, ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	5200	MPa	ISO 527-2/1
Tensile Strength			
Yield ¹	80.0	MPa	ASTM D638
Yield	74.0	MPa	ISO 527-2/5
Yield	82.0	MPa	ISO 527-2/50
Flexural Modulus			
-- ²	3600	MPa	ASTM D790
-- ³	3800	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	8.0	kJ/m ²	ISO 179
Notched Izod Impact			
23°C	83	J/m	ASTM D256
-40°C	7.0	kJ/m ²	ISO 180

23°C	8.0	kJ/m ²	ISO 180
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, not annealed	158	°C	ASTM D648
0.45 MPa, not annealed	157	°C	ISO 75-2/B
1.8 MPa, not annealed	146	°C	ISO 75-2/A
1.8 MPa, not annealed	138	°C	ISO 75-2/Af
Additional Information			
Tested at 23 ± 2°C (73.4 ± 3.6°F) and 50 ± 5% relative humidity unless otherwise noted			
NOTE			
1.	50 mm/min		
2.	1.3 mm/min		
3.	2.0 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

