# SABIC® PPcompound 8650MB1

### Polypropylene

Saudi Basic Industries Corporation (SABIC)

#### Message:

SABIC® PPcompound 8650MB1 is a development grade, elastomer-modified mineral filled Polypropylene for painted automotive exterior applications. When mixed together with 8650MB2 (in ratio 33/67) the property profile of SABIC PPcompound 8650 (see datasheet 8650U) will be reached. SABIC® PPcompound 8650MB1 is a designated automotive grade.

General Information			
Filler / Reinforcement	Mineral filler, 33% filler by weight		
Additive	Impact modifier		
Features	Impact modification		
	Sprayable		
Uses	Application in Automobile Field		
	Automotive exterior parts		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	7.0	g/10 min	ISO 1133
"9 <i>i</i>	7.0	9/ 10 111111	150 1155

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

