

EPLAMID 66 FX2 NC

Polyamide 66

EPSAN Plastik SAN. ve TiC. A.S.

Message:

Flame retardant polyamide 66 for injection moulding.
Halogen free flame retardant grade, compliance with RoHs derivatives, with rating UL94 V2 and glow-wire at 850°C, which is used in many sectors of industry.
This material is available in natural and in colours on request.

General Information				
Additive	Flame retardancy			
Features	Halogen-free			
	Flame retardancy			
RoHS Compliance	RoHS compliance			
Appearance	Available colors			
	Natural color			
Processing Method	Injection molding			
Physical	Dry	Conditioned	Unit	Test Method
Density (23°C)	1.15	--	g/cm ³	ISO 1183
Molding Shrinkage				ISO 294-4
Vertical flow direction: 3.00mm	0.80	--	%	ISO 294-4
Flow direction: 3.00mm	0.50	--	%	ISO 294-4
Moisture Content	0.20	--	%	ISO 15512
Hardness	Dry	Conditioned	Unit	Test Method
Durometer Hardness (Shore D, 23°C)	80	--		ISO 868
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus (23°C)	3500	3100	MPa	ISO 527-2/50
Tensile Stress (Break, 23°C)	60.0	50.0	MPa	ISO 527-2/50
Tensile Strain (Break, 23°C)	4.0	10	%	ISO 527-2/50
Flexural Modulus ¹ (23°C)	3300	2900	MPa	ISO 178
Flexural Stress ² (23°C)	100	90.0	MPa	ISO 178
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength (23°C)	6.0	8.0	kJ/m ²	ISO 179/1eA
Notched Izod Impact (23°C)	5.0	7.0	kJ/m ²	ISO 180/1A
Thermal	Dry	Conditioned	Unit	Test Method
Melting Temperature (DSC)	255	--	°C	ISO 3146

Electrical	Dry	Conditioned	Unit	Test Method
Comparative Tracking Index (Solution A)	300	--	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating (1.60 mm)	V-2	--		UL 94, IEC 60695-11-10, -20
Glow Wire Flammability Index (1.60 mm)	850	--	°C	IEC 60695-2-12
Glow Wire Ignition Temperature (0.800 mm)	750	--	°C	IEC 60695-2-13
Additional Information				
干燥 TEST CONDITIONS: Laboratory conditions are 23 ±2°C and 45-55 % RH.				
Injection	Dry	Unit		
Drying Temperature	80.0	°C		
Drying Time	2.0 - 4.0	hr		
Processing (Melt) Temp	280	°C		
NOTE				
1.	2.0 mm/min			
2.	2.0 mm/min			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

