

# LITEN BB 29 H

Linear Polyethylene Copolymer

UNIPETROL RPA

## Message:

LITEN BB 29 H is a linear polyethylene, copolymer with broad molecular weight distribution, suitable for blow moulding and extrusion. This grade exhibits an excellent balance among processability, stiffness and ESC resistance. Typical application is manufacture of technical parts.

LITEN BB 29 H meets the hygienic requirements on materials and articles intended for contact with foodstuffs according to Regulation (EC) 1935/2004 of the European Parliament and of the Council, as well as according to Commission Regulation (EU) No 10/2011 including changes and additions.

General Information			
Features	Copolymer		
	Food Contact Acceptable		
	Good Processability		
	Good Stiffness		
	High ESCR (Stress Crack Resist.)		
	Med.-Wide Molecular Weight Distrib.		
Uses	Blow Molding Applications		
	Engineering Parts		
Agency Ratings	EC 1935/2004		
	EU 10/2011		
Processing Method	Blow Molding		
	Extrusion		
Physical	Nominal Value	Unit	Test Method
Density	0.955	g/cm <sup>3</sup>	ISO 1183
Melt Mass-Flow Rate (MFR)			ISO 1133
190°C/2.16 kg	0.25	g/10 min	
190°C/21.6 kg	25	g/10 min	
190°C/5.0 kg	1.2	g/10 min	
Environmental Stress-Cracking Resistance (50°C, 100% Detergent, F50)	100	hr	ASTM D1693
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore D)	60		ISO 868
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	27.0	MPa	ISO 527-2
Tensile Strain (Yield)	9.0	%	ISO 527-2
Flexural Modulus	1250	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method

Charpy Notched Impact Strength			ISO 179
-30°C	5.0	kJ/m <sup>2</sup>	
23°C	10	kJ/m <sup>2</sup>	
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	125	°C	ISO 306

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

