

Nylene® 2401 HSSP BK

Polyamide 6

Custom Resins Group

Message:

High viscosity nylon copolymer with enhanced impact and high flexibility

Optimized with good melt strength for high line speeds in thin wall sections

Specifically designed for the convoluted tubing industry, but can also be used for other extrusions and some molded parts.

General Information	
Features	Copolymer Good Flexibility Good Impact Resistance Good Melt Strength High Viscosity
Uses	Tubing
Processing Method	Extrusion Injection Molding

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.06	g/cm ³	ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (23°C)	46.0	MPa	ASTM D638
Tensile Elongation (Break, 23°C)	130	%	ASTM D638
Flexural Modulus (23°C)	1370	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	150	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	40.0	°C	ASTM D648
Peak Melting Temperature	249	°C	ASTM D3418

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

