

AKROMID® B3 GF 15 S1 black (1270)

Polyamide 6
AKRO-PLASTIC GmbH

Message:

AKROMID® B3 GF 15 S1 black (1270) is a 15% glass fibre reinforced, cold impact strength polyamide 6 with medium stiffness and strength
Applications are highly integrated housings in the automotive, electro and furniture industry

General Information				
Filler / Reinforcement		Glass Fiber,15% Filler by Weight		
Features		Good Stiffness		
		Low Temperature Impact Resistance		
		Medium Strength		
Uses		Automotive Applications		
		Electrical/Electronic Applications		
		Furniture		
		Housings		
Appearance		Black		
Resin ID (ISO 1043)		PA6-I GF15		
Physical	Dry	Conditioned	Unit	Test Method
Density (23°C)	1.22	--	g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR) (275°C/5.0 kg)	45.0	--	cm ³ /10min	ISO 1133
Humidity Absorption - 62% RH (70°C)	2.3	--	%	ISO 1110
Reinforcement Content	15	--	%	ISO 1172
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	5800	3000	MPa	ISO 527-2/1
Tensile Stress (Break)	115	70.0	MPa	ISO 527-2/5
Tensile Strain (Break)	3.5	10	%	ISO 527-2/5
Flexural Modulus ¹	6000	--	MPa	ISO 178
Flexural Stress ²	190	--	MPa	ISO 178
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-30°C	5.0	5.0	kJ/m ²	
23°C	6.0	15	kJ/m ²	
Charpy Unnotched Impact Strength				ISO 179/1eU
-30°C	50	45	kJ/m ²	
23°C	70	95	kJ/m ²	

Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	200	--	°C	ISO 75-2/A
Melting Temperature ³	222	--	°C	DIN EN 11357-1
Flammability	Dry	Conditioned	Unit	Test Method
Burning Rate ⁴ (1.00 mm)	< 100	--	mm/min	FMVSS 302
Flame Rating (1.60 mm)	HB	--		UL 94
NOTE				
1.	2.0 mm/min			
2.	2.0 mm/min			
3.	10 K/min, DSC			
4.	> 1 mm			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

