

MAJORIS FFRH260R

Polypropylene
AD majoris

Message:

FFRH260R is a flame retardant with halogen compound and UL 94 VO classification, RoHS conform, intended for injection moulding. The product is available in natural (FFRH260R) but other colours can be provided on request.

APPLICATIONS

FFRH260R is intended for the injection moulding of electrical component such as:

Electrical appliance components

Sockets

Interior electrical boxes

Junction boxes

Switches and connector housings

General Information			
Additive	Flame retardancy		
Features	Recyclable materials		
	Halogenated		
	Flame retardancy		
Uses	Electrical components		
	Electrical housing		
	Home appliance components		
RoHS Compliance	RoHS compliance		
Appearance	Available colors		
	Natural color		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.36	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	20	g/10 min	ISO 1133
Molding Shrinkage	0.90 - 1.1	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	21.0	MPa	ISO 527-2/50
Flexural Modulus ¹	2400	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1A
-30°C	3.0	kJ/m ²	ISO 179/1A
23°C	6.0	kJ/m ²	ISO 179/1A
Thermal	Nominal Value	Unit	Test Method

Heat Deflection Temperature (0.45 MPa, Unannealed)	122	°C	ISO 75-2/B
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.60 mm)	V-0		UL 94
Glow Wire Flammability Index (1.00 mm)	960	°C	IEC 60695-2-12
Injection	Nominal Value	Unit	
Drying Temperature	80.0	°C	
Drying Time	3.0	hr	
Processing (Melt) Temp	210 - 240	°C	
Mold Temperature	30.0 - 50.0	°C	
Injection Rate	Moderate		
Injection instructions			
Holding pressure: 50 to 70% of the injection pressure			
NOTE			
1.	2.0 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

