

Mafill® CR XG 5544

Polypropylene

Ravago Group

Message:

PP Black GF30

General Information			
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
Recycled Content	Yes		
Appearance	Black		
Physical	Nominal Value	Unit	Test Method
Density	1.13	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	10	g/10 min	ISO 1133
Molding Shrinkage	0.35 to 0.70	%	Internal Method
Ash Content	30	%	ISO 3451
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	5500	MPa	ISO 527-2
Tensile Stress (Yield)	60.0	MPa	ISO 527-2
Flexural Modulus	4700	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength			ISO 180/1A
-20°C	4.0	kJ/m ²	
23°C	9.0	kJ/m ²	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT