

LNP™ THERMOCOMP™ KZ001L compound

Acetal (POM) Copolymer

SABIC Innovative Plastics

Message:

LNP THERMOCOMP KZ001L is a compound based on Acetal Copolymer resin containing Glass Fiber. Added features of this material include: Low Extractible.
Also known as: LNP* THERMOCOMP* Compound KF-1001 LE M
Product reorder name: KZ001L

General Information			
Filler / Reinforcement	Glass fiber reinforced material		
Features	Low extract		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.42	g/cm ³	ASTM D792, ISO 1183
Molding Shrinkage			
Flow: 24 hours	2.0 - 4.0	%	ASTM D955
Transverse flow: 24 hours	2.0 - 4.0	%	ASTM D955
Vertical flow direction: 24 hours	2.6	%	ISO 294-4
Flow direction: 24 hours	2.9	%	ISO 294-4
Water Absorption (24 hr, 50% RH)	0.20	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	2760	MPa	ASTM D638
--	2840	MPa	ISO 527-2/1
Tensile Strength			
Yield	57.9	MPa	ASTM D638
Yield	59.0	MPa	ISO 527-2
Fracture	54.5	MPa	ASTM D638
Fracture	55.0	MPa	ISO 527-2
Tensile Elongation			
Yield	9.1	%	ASTM D638
Yield	9.9	%	ISO 527-2
Fracture	27	%	ASTM D638
Fracture	43	%	ISO 527-2
Flexural Modulus			
--	2070	MPa	ASTM D790
--	2000	MPa	ISO 178
Flexural Stress	72.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			

23°C	53	J/m	ASTM D256
23°C ²	5.2	kJ/m ²	ISO 180/1A
Unnotched Izod Impact			
23°C	1300	J/m	ASTM D4812
23°C ³	84	kJ/m ²	ISO 180/1U
Instrumented Dart Impact			
23°C, Energy at Peak Load	7.40	J	ASTM D3763
--	1.60	J	ISO 6603-2
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, unannealed, 3.20mm	156	°C	ASTM D648
0.45 MPa, unannealed, 64.0mm span ⁴	148	°C	ISO 75-2/Bf
1.8 MPa, unannealed, 3.20mm	101	°C	ASTM D648
1.8 MPa, unannealed, 64.0mm span ⁵	93.0	°C	ISO 75-2/Af
Linear thermal expansion coefficient			ASTM E831, ISO 11359-2
Flow: -40 to 40°C	1.1E-4	cm/cm/°C	ASTM E831, ISO 11359-2
Lateral: -40 to 40°C	1.1E-4	cm/cm/°C	ASTM E831, ISO 11359-2
Injection	Nominal Value	Unit	
Drying Temperature	82.2	°C	
Drying Time	4.0	hr	
Rear Temperature	177 - 188	°C	
Middle Temperature	193 - 204	°C	
Front Temperature	210 - 221	°C	
Processing (Melt) Temp	199 - 216	°C	
Mold Temperature	82.2 - 110	°C	
Back Pressure	0.172 - 0.344	MPa	
Screw Speed	30 - 60	rpm	
NOTE			
1.	50 mm/min		
2.	80*10*4		
3.	80*10*4		
4.	80*10*4 mm		
5.	80*10*4 mm		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

