# Zhongfa PP ZF-T30

## Polypropylene

### Yuyao Zhongfa Engineering Plastics Co. Ltd.

#### Message:

Zhongfa PP ZF-T30 is a polypropylene material, which contains 30% talc filler. This product is available in the Asia-Pacific region and is processed by injection molding. The main features of Zhongfa PP ZF-T30 are: high gloss insulation Good dimensional stability Heat resistance Typical application areas include: electrical appliances Furniture

General Information				
Filler / Reinforcement	Talc filler, 30% filler by weight			
Features	Good dimensional stability			
	Highlight			
	Insulation			
	Good liquidity			
	Heat resistance, medium			
Uses	Electrical appliances			
	Furniture			
Forms	Particle			
Processing Method	Injection molding			
Physical	Nominal Value	Unit	Test Method	
Specific Gravity	1.20	g/cm <sup>3</sup>	ASTM D792	
Melt Mass-Flow Rate (MFR)	4.0	g/10 min	ASTM D1238	
Molding Shrinkage - Flow	0.80 - 1.0	%	ASTM D955	
Hardness	Nominal Value	Unit	Test Method	
Rockwell Hardness (R-Scale)	100		ASTM D785	
Mechanical	Nominal Value	Unit	Test Method	
Tensile Strength	50.0	MPa	ASTM D638	
Tensile Elongation (Break)	5.0	%	ASTM D638	
Flexural Modulus	2400	MPa	ASTM D790	
Flexural Strength	40.0	MPa	ASTM D790	
Thermal	Nominal Value	Unit	Test Method	
Deflection Temperature Under Load			ASTM D648	
0.45 MPa, not annealed	155	°C	ASTM D648	
1.8 MPa, not annealed	135	°C	ASTM D648	

#### Additional Information

Aging Resistance at 150°C: 750 hrNotched Izod Impact, ASTM D256: 4 kJ/m <sup>2</sup> Unnotched Izod Impact, ASTM D256: 18 kJ/m <sup>2</sup>
---

Injection	Nominal Value	Unit
Drying Temperature	90.0 - 95.0	°C
Drying Time	2.0 - 3.0	hr
Processing (Melt) Temp	195 - 225	°C
Mold Temperature	45.0 - 80.0	°C
Injection Pressure	60.0 - 90.0	MPa

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

