

RTP 2200 HF Z

Polyetheretherketone

RTP Company

Message:

FDA Compliant Ingredients

General Information			
RoHS Compliance	Contact manufacturer		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.30	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.20 mm)	1.4	%	ASTM D955
Moisture Content	0.10	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	3790	MPa	ASTM D638
Tensile Strength	93.1	MPa	ASTM D638
Tensile Elongation (Yield)	> 10	%	ASTM D638
Flexural Modulus	3790	MPa	ASTM D790
Flexural Strength	159	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.20 mm)	43	J/m	ASTM D256
Unnotched Izod Impact (3.20 mm)	1300	J/m	ASTM D4812
Injection	Nominal Value	Unit	
Drying Temperature	149	°C	
Drying Time	3.0	hr	
Dew Point	-29	°C	
Processing (Melt) Temp	349 - 399	°C	
Mold Temperature	121 - 177	°C	
Injection Pressure	82.7 - 124	MPa	
Injection instructions			

Desiccant Type Dryer Required.

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

